

CARBO 29/9 MPR

 International Standards
 Material No.
 1.4337

 EN ISO 3581-A
 E 29 9 R 53

 AWS A 5.4
 E312-26

 DIN EN 14700
 E Fe 11-UM-200-CKRTZ

Typical applications and characteristics CARBO 29/9 MPR is an AC weldable electrode with 160% recovery, suitable for joining difficult-to-weld steels. Austenitic-ferritic stainless steel welding deposit (high ferrite content). The weld metal remains ferritic, even after dilution with an austenitic base metal forming elements such as Mn, Ni und C and is thus highly crack resistant. Plastic weld metal of high tensile strength, impact proof, tough, and acid and heat resistant up to 1,000° C. Hardness after strain-hardening: ca. 360 HB Soft, intense fusion, easy slag removal, finely rippled beads. Suitable for AC welding. Joint weld with a short arc using stringer bead techniques. Maximum wall thickness < 30 mm. The weld metal alloy strain-hardens during use.

Operating temperature 20°C up to 300°C

Base materials Difficult-to-weld base materials such as: high-carbon steel, tool steel, spring steel, manganese steel, case-hardening steel, high-speed steels, cast steels, screening steels, Suitable for joining these materials to each other or to dissimilar steels. Also suitable for surfacing and repair welding rails, shafts, couplings, impellers, hot work tools, pressing and trimming tools, as well as stamping dies.

Mechanical properties of all-weld metal (typical values	Tensile strength Rm N/mm²	Yield strenght Rp0,2 N/mm ²	Elongation A5 %	Impact strenght DVM J at + 20°C	Hardness HB
	800	580	20	30	ca. 200
Weld metal analysis	С	Si	Mn	Cr	Ni
(typical, wt %)	0,10	1,2	0,7	29,0	9,5
				·	

Current

= + / ~ , 42 V

Welding positions PA, PB

Rebaking

1 h, 350° C + / - 10° C (if nacessary)

Dia./Length	Amperage (A)	Pcs./packet	Pcs./carton	kg /1000 pcs.	kg / packet	kg / carton
2,0 x 300	45 - 75	230	920	17,4	4,0	16,0
2,5 x 350	60 - 100	157	629	31,8	5,0	20,0
3,2 x 350	90 - 130	93	372	53,7	5,0	20,0
4,0 x 450	140 - 190	57	292	104,6	5,0	20,0
5,0 x 450	160 - 230	37	147	163,4	6,0	24,0

Rev. 001 / 17

Statements on composition and application are just for the applier.s information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.